

# SILBIONE® HCRA 4500 SERIES

Medical Grade High Consistency Rubber

Technical Data Sheet – December 2018

## Description

**SILBIONE® HIGH CONSISTENCY RUBBERS (HCRs)** are two-component platinum-catalyzed silicone elastomers designed for extruding medical parts.

Available in a full range of hardnesses from 20 to 80 durometer – Shore A, Elkem Silicones' **SILBIONE® HCRs** offer the distinctive advantages of easy processing and easy release combined with high performance physical properties.

## Advantages

- Easy to mill and extrude
- Rapid cure at elevated temperatures
- Good clarity
- Can be post-cured, but post-cure is not necessary to achieve desired physical properties
- Manufactured and packaged in ISO certified controlled environments

## Processing

**SILBIONE® HCRs** are supplied as kit-matched products. Parts A and B components are designed to be mixed with standard mill, extruder, or injection molding processing equipment and techniques.

### Cure:

Cure is initiated once the two-part part A and part B components are mixed and can be accelerated by heating the mixed elastomer. Cure is dependent upon temperature and part or profile size.

Special care must be taken to assure clean mixers, mills, dies, molds and a clean work area with no organic rubbers used on the same processing equipment.

*Caution: Traces of foreign materials can poison the catalyst and inhibit the cure. All metering and mixing equipment should be thoroughly cleaned. Polymer systems, which contain traces of amines, sulfur, nitrogen oxide, organotin compounds and carbon monoxide can interfere with the cure of this product and should be avoided.*

Note: Kit matching, accurate measuring and complete mixing are essential factors in obtaining consistent results.

# SILBIONE® HCRA 4500 SERIES

## TYPICAL PROPERTIES

### AS SUPPLIED

<i>Typical properties</i>	ASTM	HCRA 4520	HCRA 4530	HCRA 4540	HCRA 4550	HCRA 4560	HCRA 4565	HCRA 4570	HCRA 4580
Appearance	TP 038	Clear	Clear	Clear	Clear	Clear	Clear	Clear	Clear
Mix Ratio	-	1:1	1:1	1:1	1:1	1:1	1:1	1:1	1:1
Specific Gravity	TP 013	1.11	1.12	1.13	1.14	1.15	1.17	1.18	1.2

### PRESS CURE, 15 minutes, 177°C (350°F), Cold Mold

<i>Typical properties</i>	ASTM	HCRA 4520	HCRA 4530	HCRA 4540	HCRA 4550	HCRA 4560	HCRA 4565	HCRA 4570	HCRA 4580
Hardness, Shore A	D2240	20	30	40	50	60	65	70	80
Tensile strength, Psi	D412	1250	1700	1650	1650	1550	1500	1450	1250
Elongation, %	D412	1000	1000	975	950	775	725	700	650
Tear strength, Ppi	D624 Die B	225	250	250	300	265	250	235	225
Work Life, hr	D412	2	3	4	4	4	4	4	4

### CURE KINETICS, MDR, 5 minutes, 115°C (240°F)

<i>Typical properties</i>	ASTM	HCRA 4520	HCRA 4530	HCRA 4540	HCRA 4550	HCRA 4560	HCRA 4565	HCRA 4570	HCRA 4580
t <sub>2</sub> , minutes	D5289	0.2	0.15	0.2	0.2	0.15	0.15	0.15	0.15
t <sub>90</sub> , minutes	D5289	0.5	0.5	0.5	0.5	0.3	0.3	0.3	0.3
Prate, lb/min	D5289	30	40	45	55	65	80	85	120

**Please note:** The typical properties listed in this bulletin are not intended for use in preparing specifications for any application of SILBIONE® silicone materials.

Visit us at <https://silicones.elkem.com>

# SILBIONE® HCRA 4500 SERIES

## Regulation

### Biocompatibility Testing

Designed specifically for long-term implant applications, **SILBIONE®** brand materials have been tested according to, or are substantially equivalent to, materials that have been tested according to ISO 10993/USP Class VI for:

- Cytotoxicity
- Skin Sensitization
- Skin Irritation (ISO 10993)

### Limitation

The purchaser has the sole responsibility to select an Elkem Silicones product and determine its application suitability. The purchaser also has the sole responsibility to comply with all applicable statutory, regulatory and industry requirements and standards for compatibility, extractability, testing, safety, efficacy and labelling.

## Packaging

**SILBIONE® HCRs** are available in:

- 5 kg and 20 kg Kits. Each containing equal portions of Part A and Part B.

## Storage and shelf life

When stored in their original packaging at a temperature of between 5°C (40°F) and 32°C (90°F), **SILBIONE® HCRs** may be stored for up to 1 year from their date of manufacture. Comply with the storage instructions and expiry date marked on the packaging.

Beyond this date, Elkem Silicones no longer guarantees that the products meet the sales specifications.

## Safety

Please consult the Safety Data Sheets of **SILBIONE® HCRs**.

### EUROPE

Elkem Silicones France  
21 Avenue Georges Pompidou  
F69486 Lyon Cedex 03  
FRANCE  
Tel. (33) 4 72 13 19 00  
Fax (33) 4 72 13 19 88

### NORTH AMERICA

Elkem Silicones USA  
2 Tower Center Boulevard  
Suite 1601  
East Brunswick, NJ 08816-1100  
United States  
Tel. (1) 732 227-2060  
Fax. (1) 732 249-7000

### LATIN AMERICA

Elkem Silicones Brazil Ltda.  
Av. Duquesa de Goiás, 716  
2º andar  
05680-002 Sao Paulo  
Brazil  
Tel. (55) 11 4380-6900

### ASIA PACIFIC

Elkem Silicones Hong Kong  
Trading Co. Ltd  
29th Floor, 88 Hing Fat Street  
Causeway Bay  
Hong Kong  
Tel. (852) 3106 8200  
Fax (852) 2979 0241

### Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.